Report No:SCEPL/MT/Jun/02/01/01/2020-21

Date:07.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/02/01
Agency	KRIDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	02.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	May/31/01-01	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	445.9	19.82	19.43
	May/31/01-02	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	426.7	18.98	
	May/31/01-03	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	438.5	19.50	
2	May/31/01-04	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	455.9	20.26	20.03
	May/31/01-05	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	441.7	19.64	
	May/31/01-06	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	453.5	20.17	
3	May/31/01-07	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	464.9	20.66	20.31
	May/31/01-08	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	456.7	20.31	
	May/31/01-09	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	448.5	19.95	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA CONSULTIG ENGINEER PVT LTD Bangalore

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

Sunitha.N.K
AE-10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishweshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com |

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/May/28/01/01/2020-21 Date:02.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020/May/28/01
Agency	KRIDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	28.05.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	May/26/01-01	26.05.2020	02.06.2020	150.0	150.0	149.9	22500	8.050	465.9	20.71	20.17
	May/26/01-02	26.05.2020	02.06.2020	150.0	149.9	150.0	22485	8.100	426.7	18.98	
	May/26/01-03	26.05.2020	02.06.2020	149.9	150.0	149.8	22485	8.250	468.5	20.84	
2	May/26/01-04	26.05.2020	02.06.2020	150.0	150.0	149.9	22500	8.050	455.9	20.26	20.28
	May/26/01-05	26.05.2020	02.06.2020	150.0	150.9	150.0	22635	8.100	461.7	20.40	
	May/26/01-06	26.05.2020	02.06.2020	149.9	150.0	149.8	22485	8.250	453.5	20.17	
3	May/26/01-07	26.05.2020	02.06.2020	150.0	150.0	149.9	22500	8.050	464.9	20.66	20.31
	May/26/01-08	26.05.2020	02.06.2020	150.0	149.9	150.0	22485	8.100	456.7	20.31	
	May/26/01-09	26.05.2020	02.06.2020	149.9	150.0	149.8	22485	8.250	448.5	19.95	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

CONSULTING ENGINEER Bangalore

AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com |

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/02/01/01/2020-21

Date:07.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/02/02
Agency	KRIDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	02.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
4	May/31/01-10	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	445.9	19.82	19.43
	May/31/01-11	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	426.7	18.98	
	May/31/01-12	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	438.5	19.50	
5	May/31/01-13	31.05.2020	07.06.2020	150.0	150.0	149.9	22500	8.050	455.9	20.26	20.03
	May/31/01-14	31.05.2020	07.06.2020	150.0	149.9	150.0	22485	8.100	441.7	19.64	
	May/31/01-15	31.05.2020	07.06.2020	149.9	150.0	149.8	22485	8.250	453.5	20.17	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

SHIPRAMA CONSULTING ENGINEER PVT. LTD. Bangalore

Page 1/1

Sweetha-NK
AE W10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Visveshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com |

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/02/01/01/2020-21 Date:28.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/02/01
Agency	KRIDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	02.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	May/31/01-16	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.12
	May/31/01-17	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	680.7	30.27	
	May/31/01-18	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
2	May/31/01-19	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	669.9	29.77	29.84
	May/31/01-20	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	672.7	29.92	
	May/31/01-21	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	670.5	29.82	
3	May/31/01-22	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	670.9	29.82	30.13
	May/31/01-23	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	692.7	30.81	
	May/31/01-24	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	669.5	29.78	

Remarks:-

- The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

CONSULTIG ENGINEERS (P) LTD Bangalore

AE/JE

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com |

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/02/01/01/2020-21

Date:28.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/02/02
Agency	KRIDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	02.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
4	May/31/01-25	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.12
	May/31/01-26	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	680.7	30.27	
	May/31/01-27	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
5	May/31/01-28	31.05.2020	28.06.2020	150.0	150.0	149.9	22500	8.050	670.9	29.82	30.13
	May/31/01-29	31.05.2020	28.06.2020	150.0	149.9	150.0	22485	8.100	692.7	30.81	
	May/31/01-30	31.05.2020	28.06.2020	149.9	150.0	149.8	22485	8.250	669.5	29.78	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

CONSULTING ENGINEERS Bangalore

Page 2/2

Suvetha.NL
AE(W)10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com |

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/05/01/01/2020-21 Date:09.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/05/01
Agency	KRIDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	05.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	Jun/02/01-01	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.150	445.9	19.82	19.43
	Jun/02/01-02	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.700	426.7	18.98	
	Jun/02/01-03	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.250	438.5	19.50	
2	Jun/02/01-04	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.450	455.9	20.26	20.03
	Jun/02/01-05	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.160	441.7	19.64	
	Jun/02/01-06	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.250	453.5	20.17	
3	Jun/02/01-07	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.350	464.9	20.66	20.31
	Jun/02/01-08	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.210	456.7	20.31	
	Jun/02/01-09	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.250	448.5	19.95	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA CONSULTING ENGINEER PVT. LTD. Bangalore

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

Suvitha. N.L
AEW10

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com |

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/05/01/01/2020-21 Date:09.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020-Jun/05-02
Agency	KRIDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	05.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
4	Jun/02/01-10	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.050	445.9	19.82	20.03
	Jun/02/01-11	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.310	446.7	19.87	
	Jun/02/01-12	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.250	458.5	20.39	
5	Jun/02/01-13	02.06.2020	09.06.2020	150.0	150.0	149.9	22500	8.150	455.9	20.26	20.03
	Jun/02/01-14	02.06.2020	09.06.2020	150.0	149.9	150.0	22485	8.100	441.7	19.64	
	Jun/02/01-15	02.06.2020	09.06.2020	149.9	150.0	149.8	22485	8.350	453.5	20.17	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

CONSULTIG ENGINEERS PRIVATE LIMITED Bangalore

Page 2/2

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/05/01/01/2020-21 Date:30.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/05/01
Agency	KRIDL
Date of Receipt:	05.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	Jun/02/01-16	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.050	690.9	30.71	30.62
	Jun/02/01-17	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.125	680.7	30.27	
	Jun/02/01-18	02.06.2020	30.06.2020	149.9	150.0	149.8	22485	8.250	694.5	30.89	
2	Jun/02/01-19	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.050	699.9	31.11	31.02
	Jun/02/01-20	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.100	702.7	31.25	
	Jun/02/01-21	02.06.2020	30.06.2020	149 9	150.0	149.8	22485	8.350	690.5	30.71	
3	Jun/02/01-22	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.500	698.9	31.06	31.14
	Jun/02/01-23	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.000	692.7	30.81	
	Jun/02/01-24	02.06.2020	30.06.2020	149.9	150.0	149.8	22485	8.255	709.5	31.55	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

CONSULTIG ENGINEER Bangalore

Suvetha. N L AEW10

Assistant Executive Engineer Vidyaranyapura Sub Division BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com |

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/05/01/01/2020-21 Date:30.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/05/02
Agency	KRIDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	05.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/28 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

SL No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
4	Jun/02/01-25	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.300	690.9	30.71	30.12
	Jun/02/01-26	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.200	680.7	30.27	
	Jun/02/01-27	02.06.2020	30.06.2020	149.9	150.0	149.8	22485	8.250	660.5	29.38	
5	Jun/02/01-28	02.06.2020	30.06.2020	150.0	150.0	149.9	22500	8.050	669.9	29.77	29.84
	Jun/02/01-29	02.06.2020	30.06.2020	150.0	149.9	150.0	22485	8.100	672.7	29.92	
	Jun/02/01-30	02.06.2020	30.06.2020	149.9	150.0	149.8	22485	8.230	670.5	29.82	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

SHIPRAMA Consulting Engineers Pvt. Ltd. ★ Bangalore

Authorized Signatory

SHIPRAMA CONSULTING ENGINEERS PVT. LTD. Bangalore

Suvetha. N L
AE W10

Page 1/1

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com |

Scanned with CamScanner

SHIPRAMA CONSULTING ENGINEERS PRIVATE LIMITED

(Mechanical Testing Laboratory Division)

ISO 9001:2015

Report No:SCEPL/MT/Jun/12/01/01/2020-21 Date:17.06.2020

TEST REPORT

*Client Name& Address:	Asst. Executive Engineer Vidyaranya Pura Sub Division BBMP, Bangalore.
*Name of Work:	Improvements to Roads and Drains at Byarappa Garden, KNE College 4th Block,Kateramma Layout cross Roads in ward No 10 Doddabommasandra
*Letter Reference:	No:BBMP/EE/BTP/WO/209/2019-20 Dated-10.03.2020
SCEPL ID	SCEPL/MT/2020/Jun/12/01
Agency	KRIDL
Source of Sample:	Samples supplied by the Customer
Date of Receipt:	12.06.2020
Sample Type/Size/ Grade/Age:	CC Cubes/150mmx150mmx150mm/7 days Compressive Strength
Reference to BIS codes:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
*Grade of concrete	M30
*Location	CC Pavement

Compressive strength of Concrete cube

Sl. No.	Identification mark	Date of Casting	Date of Testing	Dimension of the Specimen mm			Cross sectional area (Sq.mm)	Weight (kg)	Failure Load (kN)	Compressive strength (N/mm2)	Average Compressive Strength (N/mm^2)
				L	B	H					
1	Jun/10/01-01	10.06.2020	17.06.2020	150.0	150.0	149.9	22500	8.350	426.7	18.96	19.58
	Jun/10/01-02	10.06.2020	17.06.2020	150.0	149.9	150.0	22485	8.200	438.5	19.50	
	Jun/10/01-03	10.06.2020	17.06.2020	149.9	150.0	149.8	22485	8.250	455.9	20.28	
2	Jun/10/01-04	10.06.2020	17.06.2020	150.0	150.0	149.9	22500	8.050	441.7	19.63	20.16
	Jun/10/01-05	10.06.2020	17.06.2020	150.0	149.9	150.0	22485	8.100	453.5	20.17	
	Jun/10/01-06	10.06.2020	17.06.2020	149.9	150.0	149.8	22485	8.300	464.9	20.68	

Remarks:-

The results pertain to the samples received and tested.

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

* Information furnished by the client

*** End of the report***

Shiprama Consulting Engineers Pvt. Ltd. Bangalore

Authorized Signatory

BVH Consultig Engineers Pvt. Ltd. Bangalore

Suvetha.N.L AEW

Page 1/1

Assistant Executive Engineer Vidyaranyapura Sub Division BBMP, Bangalore-97

1048, 8th Block Extension ,Gangubai Hangal Road, Sir M. Vishveshwaraiah Layout, Near Gidadakonenahalli
Bengaluru-560091.Mob:9886212878 Ph.: 080 29554444 | Email: shiprama888@gmail.com |

Scanned with CamScanner